

# Product-Data-Sheet. RADDITRANS T

### Description of the product

RADDITRANS binder compounds are calcium sulfate binders according to EN 13454-1 and are suitable for the production of high-quality self-levelling (flowing) floor screeds transported to site by means of ready mix trucks.

RADDITRANS T is based on thermal anhydrite and is suitable for bonded screed, screed laid on a separating layer (unbonded), floating screed and heated floor screed constructions.

Depending on aggregate and mix design different strength classes can be achieved.

Due to its very long working time RADDITRANS T is suitable for the production of screed material in ready-mix plants.

### Information

This product data sheet is to provide advice to the best of our knowledge and replaces all previous data sheets.

However, its content has no legally binding effect.

### For further information,

#### please contact:

CASEA GmbH  
Pontelstraße 3  
99755 Ellrich  
Deutschland  
T +49 36332 89-100  
F +49 36332 89-202  
info@casea-gips.de  
casea-gips.de

Ein Unternehmen der  
REMONDIS-Gruppe

### > Technical and physical data

flow spread diameter (Hägermann cone)	22 – 24 cm
open time as screed*	30 – 45 min after pumping
maximum travelling time in ready mix truck*	3 h
strength of binder	CAB 40 according to EN 13454
light foot traffic after*	approx. 24 h
partial load-bearing capacity after	4 days
start of heating procedure after	4 days
Reaction to fire	A 1, not burnable
pH-value	alkaline pH > 11
bulk density	approx. 1,1 kg/dm <sup>3</sup>

\*depends on climate

### > Logistic and safety

packaging	big bag and bulk
storage	6 months under dry, protected conditions
safety information	see safety sheet.

### > CE-marking



CASEA GmbH  
Pontelstraße 3  
99755 Ellrich  
Deutschland

06  
04 16911 203  
EN 13454-1: 2004, Calcium sulfate binder CAB 40  
for use internally in buildings

Reaction to fire	A1
pH-Value	≥ 7
Strength class	40
Content of calcium sulphate	≥ 85 %
Shrinkage and swelling	≤ 0,2mm/m

\*NPD No Performance Determined