

Technical Data Sheet.

Raddident 15

Description of the product

Raddident 15 is a highly pure alpha-hemihydrate which is produced based on synthetic gypsum.
Raddident 15 is particularly well suited for the production and formulation of super hard stone plasters.

Information

This product data sheet is intended to give advice to the best of our knowledge; it replaces any previous product data sheets. The contents of this product data sheet are not legally binding.

> Technical data and specifications

Gypsum/water ratio (DIN EN 13279)	0,38
Initial setting time	≥ 3 min
Residue 32 µm (Retsch Camsizer)	approx. 20 %
Degree of whiteness (Hunter-Lab)	L* ≥ 91
Bulk density	approx. 950 g/dm ³
Compressive strength	≥ 35 N/mm ²

For further information please contact:

CASEA GmbH
Pontelstraße 3
99755 Ellrich
Germany
P +49 36332 89-100
F +49 36332 89-202
info@casea-gips.de
casea-gips.de

A company of the
REMONDIS Group

> Logistics and safety notes

Commercial form	bag, big-bag and bulk
Shelf life	given dry and protected storage, Raddident 15 can be stored up to 6 months after date of shipping
Safety notes	see MSDS no specific hazards arising from Raddident 15

> CE-Kennzeichnung



CASEA GmbH
Pontelstraße 3
99755 Ellrich
Deutschland

13
CASEA-207 066
EN 13279-1: 2008, gypsum binders A1
gypsum binders for direct use or further processing

Reaction to fire	A1
Content of calcium sulphate	≥ 50%
Direct airborne sound insulation	NPD*
Acoustic absorption	NPD*
Thermal resistance	NPD*
Dangerous Substances	NPD*

*NPD = No Performance Determined