

Technical Data Sheet.

Raddident SW15

Description of the product

Raddident SW15 (super white) is a high-purity alpha-hemihydrate with a high degree of whiteness. The basis for the production is a synthetic gypsum from food production.

Raddident SW15 is well suited for the production and formulation of super hard stone plasters

Information

This product data sheet is intended to give advice to the best of our knowledge; it replaces any previous product data sheets. The contents of this product data sheet are not legally binding.

> Technical data and specifications

Gypsum/water ratio (DIN EN 13279)	0,38
Initial setting time	≥ 3 min
Residue 40 µm (Retsch Camsizer)	9 - 19 %
Degree of whiteness (Hunter-Lab)	L* ≥ 94
Bulk density	> 950 g/dm ³
Compressive strength	> 35 N/mm ²

For further information please contact:

CASEA GmbH
Pontelstraße 3
99755 Ellrich
Germany
P +49 36332 89-100
F +49 36332 89-202
info@casea-gips.de
casea-gips.de

A company of the
REMONDIS Group

> Logistics and safety notes

Commercial form	bag, big-bag and bulk
Shelf life	given dry and protected storage, Raddident SW15 can be stored up to 6 months after date of shipping
Safety notes	see MSDS no specific hazards arising from Raddident SW15

> CE-Kennzeichnung



CASEA GmbH
Pontelstraße 3
99755 Ellrich
Deutschland

13
CASEA-207 066
EN 13279-1: 2008, gypsum binders A1
gypsum binders for direct use or further processing

Reaction to fire	A1
Content of calcium sulphate	≥ 50%
Direct airborne sound insulation	NPD*
Acoustic absorption	NPD*
Thermal resistance	NPD*
Dangerous Substances	NPD*

*NPD = No Performance Determined