

Technical Data Sheet. Raddipur (S) – Calcium Sulphate

Product description

Raddipur (S) is synthetic calcium sulphate anhydrite from the hydrofluoric production to be used in formulations of calcium sulphate floor screeds, gypsum-based or gypsum-lime-based plasters or for building chemistry.

Raddipur (S) does not contain ex-factory additives.

Information

This technical data sheet is intended to give advice to the best of our knowledge; it replaces any previous technical data sheets. The contents of this technical data sheet are not legally binding.

> Technical data and specifications

Chemical average analysis	Water of crystallisation	< 0.8 %
	CaSO ₄	91-95 %
	Calciumoxide	< 3 %
	Calcium fluoride	< 3 %
Particle density	2.93 g/cm ³	
Bulk density	< 1,200 g/l	
Specific surface (Blaine)	approx. 4,000 cm ² /g	
pH value aqueous	alkaline, pH > 10	

For further information

please contact:

SYNTHECO GmbH

Werksweg 2

D-92551 Stulln

Germany

P +49 2306 106-207

F +49 2306 106-540

info@syntheco.de

syntheco.de

A company of the
REMONDIS Group

> Logistics and safety notes

Commercial form	bulk ex factory D- 92551 Stulln
Shelf life	given dry and protected storage, Raddipur (S) can be stored for 6 months from the date of delivery
Safety notes	see safety data sheet